
ZINC OXIDE:

NEW INSIGHTS INTO A

MATERIAL FOR ALL AGES

BY

AMIR MOEZZI

BSc. Chemical Engineering

A Dissertation Submitted for the

Degree of Doctor of Philosophy

University of Technology Sydney

2012

Certificate of authorship/originality

I certify that the work in this thesis has not previously been submitted for a degree nor has it been submitted as part of requirements for a degree except as fully acknowledged within the text.

I also certify that the thesis has been written by me. Any help that I have received in my research work and the preparation of the thesis itself has been acknowledged. In addition, I certify that all information sources and literature used are indicated in the thesis.

A handwritten signature in purple ink, consisting of a large, stylized 'S' shape with a horizontal line through it, followed by the initials 'A.M.' in a smaller, simpler script.

Amir Moezzi

11/10/2012

Copyright © 2012 by Amir Moezzi

All rights reserved. No part of this publication may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of the author, except in the case of brief quotations embodied in critical reviews and certain other non-commercial uses permitted by copyright law.

Printed and bound in Australia

Acknowledgements

I would like to express my special appreciation to the company PT. Indo Lysaght, of Indonesia, for financial support for my project and very kind hospitality during the visits from their chemical plants.

My greatest debts are to my principal supervisor, Prof. Michael Cortie, and my co-supervisors Dr Andrew McDonagh, who gave me the opportunity to undertake this project and for their support and encouragement throughout the project. I learned so much working with you and I am really grateful for your time and effort teaching me how to do high quality research and produce interesting and important results. I also thank you for editorial help in my thesis.

Thanks to my family for their encouragement despite a long distance between us.

Very special thank to Dr Ronald Shimmon for his extensive care and support. Also I would like to express my appreciation to Drs R. Wuhler, M. Berkahn, A. Dowd, M. Philips, C. Ton-That, P. Thomas and L. Xiao. I also thank Mr J-P. Guerbois for his help in performing TGA and MS, Mrs S. Fenech and Mrs G. Armstrong for their help in using nitrogen measurement instrument and also Mr D. Bishop for performing the ICP-MS test. Thanks to Miss V. Schrameyer for her help in translation of German papers into English.

Sincere thanks to my fellow friends specially Mr M. Coutts for their patience and listening to long and sometimes boring discussions that we had during this period.

Thanks to Drs P. Robinson (Canada), S. Mahmud (Malaysia) and P. Stamford (Australia) for their helpful responses to our questions. Thanks to Dr H. Nguyen, from School of Chemical Engineering at UNSW for some of the BET surface area measurements and Dr K. Kannangara from School of Science and Health, UWS for solid-NMR. Support from companies for providing photographs for my publication is highly appreciated. Thanks to the Microstructural Analysis Unit (MAU) at UTS for providing me with the state-of-the-art equipment and facilities to analyse the materials. Thanks to Australian Synchrotron in Melbourne for the time they provided for the synchrotron radiation studies in this work.

Last but not least, I thank all of my friends who supported me with patience in my project.

Table of Contents

	Page
Certificate of authorship/originality	ii
Acknowledgements	iii
Table of Contents	v
List of Figures	x
List of Tables	xviii
List of Schemes	xix
Abbreviations	xx
Publications and conference presentations associated with this work	xxiv
Abstract	xxv
Chapter 1: Zinc Oxide: Synthesis, Properties and Applications	2
1.1. INTRODUCTION AND OVERVIEW OF THE DISSERTATION	2
1.2. HISTORICAL ASPECTS	5
1.3. SYNTHESIS	8
1.3.1. <i>Background</i>	8
1.3.2. <i>Industrial production methods</i>	10
Pyrometallurgical synthesis	11
Hydrometallurgical synthesis	29
ZnO as a by-product from other processes	30
Production of “active” zinc oxide by decomposition of hydrozincite	31
1.3.3. <i>Small-scale production routes</i>	35
Precipitation of Zn(OH) ₂ or ZnO from aqueous solutions of zinc salts	35
Solvent extraction and pyrolysis of zinc nitrate	35
Deposition of thin films	36
Gas-phase synthesis	36
Miscellaneous other methods	37
1.4. PROPERTIES	38
1.4.1. <i>Crystal structures</i>	39
1.4.2. <i>Toxicology</i>	40
1.4.3. <i>Morphology of zinc oxide particles</i>	41
1.4.4. <i>Industrial grades</i>	42
Bulk zinc oxide	42
Active zinc oxide by calcination of a carbonate	43
Other ‘wet-process’ ZnO	43
	v

ZnO single crystals	44
1.4.5. <i>Optical properties</i>	44
1.4.6. <i>Electrical, thermal and magnetic properties</i>	45
Piezoelectricity, pyroelectricity and thermoelectricity	45
Ferroelectricity, magnetism and ferromagnetism	46
Electrical conductivity	46
Heat capacity, thermal conductivity, thermal expansion coefficient	48
Thermochromism	48
1.4.7. <i>Surface properties</i>	48
1.5. APPLICATIONS	49
1.5.1. <i>Rubber</i>	49
1.5.2. <i>Ceramics and concrete</i>	54
1.5.3. <i>Plastics and linoleum</i>	55
1.5.4. <i>Pigments and coatings</i>	56
1.5.5. <i>Cosmetics, medical and dental</i>	57
1.5.6. <i>Catalysts</i>	59
1.5.7. <i>Desulfurisation</i>	61
1.5.8. <i>Oil and gas well drilling fluid</i>	63
1.5.9. <i>Varistors</i>	63
1.5.10. <i>Fertilisers, food supplements and animal feed</i>	65
1.5.11. <i>Zinc oxide in chemical synthesis</i>	67
1.5.12. <i>Miscellaneous applications</i>	70
1.6. POTENTIAL AND EMERGING APPLICATIONS	71
1.6.1. <i>Liquid crystal displays (LCDs)</i>	71
1.6.2. <i>Light emitting diodes (LEDs)</i>	72
1.6.3. <i>Spintronics</i>	72
1.6.4. <i>Solar cells</i>	72
1.6.5. <i>Sensors and actuators</i>	73
1.6.6. <i>ZnO in textiles</i>	73
1.7. CONCLUSIONS	73
Chapter 2: Single-Stage Process to Synthesise Zinc Oxide Using Sodium Hydroxide	76
2.1. INTRODUCTION	76
2.2. EXPERIMENTAL	80
2.2.1. <i>General</i>	80
2.2.2. <i>Reactant stoichiometry</i>	81
2.2.3. <i>Method of combining the reactants</i>	81
2.2.4. <i>Reaction temperature</i>	82
2.3. RESULTS AND DISCUSSION	82
2.3.1. <i>The effect of reactant stoichiometry</i>	82

2.3.2. <i>Method of combining reactants</i>	87
2.3.3. <i>The effect of temperature</i>	90
2.3.4. <i>Fluorescence spectroscopy</i>	93
2.3.5. <i>The catalytic effect of OH</i>	95
2.4. CONCLUSIONS	98
Chapter 3: A Single-Stage Process to Synthesise Zinc Oxide Using Ammonia	100
3.1. INTRODUCTION	100
3.2. EXPERIMENTAL	101
3.3. RESULTS AND DISCUSSION	102
3.3.1. <i>Characterisation and thermogravimetric analysis</i>	102
3.3.2. <i>Microscopy and BET surface area measurement</i>	103
3.3.3. <i>Fluorescence spectroscopy</i>	105
3.3.4. <i>The catalytic role of NH₃ and OH</i>	105
3.4. CONCLUSIONS	108
Chapter 4: Multi-Stage Routes to Synthesise Zinc Oxide Using Zinc Peroxide	110
4.1. INTRODUCTION	110
4.2. EXPERIMENTAL	111
4.2.1. <i>General</i>	111
4.2.2. <i>Synthesis</i>	111
ZnO ₂ via zinc acetate and H ₂ O ₂ reaction	111
ZnO from as-synthesised ZnO ₂	111
ZnO ₂ via Zn ₄ SO ₄ (OH) ₆ ·4H ₂ O and H ₂ O ₂ reaction	112
ZnO from as-synthesised ZnO ₂	112
4.3. RESULTS AND DISCUSSION	112
4.3.1. <i>Characterisation</i>	112
Products from reaction of zinc acetate and H ₂ O ₂	112
Products from reaction of Zn ₄ SO ₄ (OH) ₆ ·4H ₂ O and H ₂ O ₂	113
4.3.2. <i>Thermogravimetric analysis</i>	114
4.3.3. <i>Mechanisms of formation of zinc peroxide</i>	115
Zinc acetate-H ₂ O ₂ route	115
Zn ₄ SO ₄ (OH) ₆ ·4H ₂ O-H ₂ O ₂ route	116
4.4. CONCLUSIONS	118
Chapter 5: Multi-Stage Routes to Synthesise Zinc Oxide Using Zinc Hydroxy Salts	120
5.1. INTRODUCTION	120
5.2. EXPERIMENTAL	121
5.2.1. <i>General</i>	121
5.2.2. <i>Synthesis of zinc hydroxy salts</i>	123
Zinc hydroxy carbonate	123

Zinc hydroxy sulphate	123
Zinc hydroxy chloride	123
Zinc hydroxy nitrate	124
Zinc hydroxy acetate	124
Product of reaction between zinc hydroxy acetate and ethanol	124
5.2.3. <i>Synthesis of ZnO from zinc hydroxy salts</i>	125
5.3. RESULTS AND DISCUSSION	125
5.3.1. <i>Zinc hydroxy carbonate</i>	125
Characterisation, TGA-DTA and microscopy	126
Real-time synchrotron radiation study	129
BET surface area measurements	130
5.3.2. <i>Zinc hydroxy sulphate</i>	132
Characterisation and TGA-DTA	132
Synchrotron radiation study and TGA-MS	134
Microscopy and BET surface area measurement	141
Mechanism	142
5.3.3. <i>Zinc hydroxy chloride</i>	143
Characterisation, BET surface area measurement and microscopy	146
Synchrotron radiation study, TGA-DTA and TGA-MS	148
TGA-MS	152
Sublimation test	153
Mechanism	156
5.3.4. <i>Zinc hydroxy nitrate</i>	157
Characterisation, BET surface area measurement and microscopy	157
Synchrotron radiation study and TGA-DTA	159
TGA-MS	161
Mechanism	169
5.3.5. <i>Zinc hydroxy acetate</i>	170
Characterisation, BET surface area measurement and microscopy	176
FTIR spectroscopy	178
CP-MAS ^{13}C NMR	180
TGA-DTA	181
Synchrotron radiation study	182
TGA-MS	186
Evidence for the formation of sublimate	191
Mechanism	193
Reactivity of zinc hydroxy acetate dihydrate with ethanol	193
5.3.6. <i>Comparison</i>	200
TGA	200
XRD	201

Fluorescence spectroscopy	202
BET specific surface area	205
5.4. CONCLUSIONS	205
Chapter 6: Mechanistic and Kinetic Aspects of the Solid/liquid Pathway for the Formation of Zinc Hydroxy Nitrate	208
6.1. INTRODUCTION	208
6.2. EXPERIMENTAL	210
6.2.1. <i>General</i>	210
6.2.2. <i>Synthesis</i>	210
6.2.3. <i>Kinetics</i>	211
6.2.4. <i>Determination of solubility of zinc hydroxy nitrate</i>	211
6.3. RESULTS AND DISCUSSION	212
6.3.1. <i>Characterisation and stoichiometry of the reaction</i>	212
6.3.2. <i>Thermodynamics</i>	217
6.3.3. <i>Kinetics</i>	222
6.3.4. <i>Solubility</i>	229
6.3.5. <i>Mechanism and catalytic role of H^+</i>	230
6.4. CONCLUSIONS	231
Chapter 7: General Conclusions and Future Directions	234
7.1. GENERAL CONCLUSIONS	234
7.2. FUTURE DIRECTIONS	236
Appendix	239
References	245

List of Figures

	Page
Figure 1.1. Number of scientific publications on zinc oxide since 1882 until 2011. Data available from literature database Scopus (keyword: “zinc oxide”).....	2
Figure 1.2. Advertisement label for zinc oxide, 1868. (USA Library of Congress. http://www.loc.gov/pictures/item/2006679062/ Reproduction Number: LC-USZ62-51233).....	8
Figure 1.3. Chart showing the various uses of zinc metal. Zinc oxide is the main chemical produced from zinc metal. Compiled using data from diverse sources.	9
Figure 1.4. Schematic of the indirect process to produce ZnO reproduced from the 1850 US patent of Leclair and Barruel [45].	12
Figure 1.5. Photograph of a French process drum in operation, by permission from PT. Indo Lysaght, Indonesia.	13
Figure 1.6. A typical bag-house design reproduced from the US patent 6786946.	14
Figure 1.7. The Metallurgical Zinc Recovery (MZR) system for the separation of metallic zinc from zinc ash. From Pyrotek technical documents [51, 52].	15
Figure 1.8. SEM images of the French process ZnO (samples from PT. Indo Lysaght, Indonesia; images by Dr R. Wuhler, University of Technology Sydney).	16
Figure 1.9. Process flow diagram (PFD) of the French process.	17
Figure 1.10. Schematic of the Larvik process designed by Lundevall [55].	18
Figure 1.11. Graph of melting and boiling points of the first transition series elements, Cd and Pb.	19
Figure 1.12. Zinc oxide rotary kiln. Picture by Henan Bailing Machinery Co. [58].	20
Figure 1.13. Ellingham diagram showing free energy change of indicated reactions as a function of temperature, calculated using standard state thermodynamic data for the species.	21
Figure 1.14. Effect of temperature and gas composition on the partial pressure of $Zn_{(g)}$ (in atm). A decrease in temperature or CO/CO_2 causes a reduction in p_{Zn} due to increased oxidation. Recalculated and redrawn after Schoukens <i>et al.</i> , [61]. Atmospheric pressure is assumed.	22
Figure 1.15. Typical process flow diagram of the Waelz process with permission from ValoRes GmbH [66]. Note: in the American process the ‘process air pipe’ shown in the PFD above is not normally used (private communication with Dr Juergen Ruetten, ValoRes GmbH).	24
Figure 1.16. Waelz kiln Sections [66].	25
Figure 1.17. Specific surface area of ZnO vs. pyrolysis temperature using zinc acetate dihydrate 32.6% (w/v) aqueous solution [49].	26
Figure 1.18. Process flow diagram (PFD) of spray pyrolysis of aqueous solution of zinc salts to ZnO. ...	26
Figure 1.19. Schematics of (left) submerged plasma process [77] and (right) Mintek’s Enviroplas process for zinc fuming [72].	28
Figure 1.20. (a) Zinc ash; (b) zinc dross. © Commonwealth of Australia 2001 [78]. Photographs courtesy of Environment Australia.	29
Figure 1.21. Schematic of the sodium dithionite process [83].	30

Figure 1.22. Free energy change for reaction $\text{Zn}_5(\text{CO}_3)_2(\text{OH})_6 \rightleftharpoons 5\text{ZnO} + 2\text{CO}_2 + 3\text{H}_2\text{O}$, calculated by the authors using published thermochemical data [88, 89].	31
Figure 1.23. Fully hydroxylated ZnO crystal [8].	33
Figure 1.24. Schematic of the rotary kiln for the calcination of basic zinc carbonate as depicted in US patent 2603554 [95].	34
Figure 1.25. Organic solvent extraction process for the production of zinc oxide [62].	36
Figure 1.26. Arc discharge method schematic, reproduced from [107].	37
Figure 1.27. Unit cell of the crystal structure of ZnO. (a) Hexagonal wurtzite structure, (b) “zinc-blende” structure and (c) cubic rock-salt structure [2].	39
Figure 1.28. SEM images of ZnO showing various morphologies; (a) and (b) are reprinted with permission from [110], (c) from [111], (d) from [99], (e) from [140], (g) from [132], (h) from [98] and (f) is synthesised by the authors. Reproduced with permission from the various sources cited.	42
Figure 1.29. Zinc oxide single crystal, produced by the hydrothermal method. Image courtesy of Tokyo Denpa Co., Ltd. Japan.	44
Figure 1.30. Mechanism for reaction of zinc oxide and the vulcanisation accelerator [193].	51
Figure 1.31. Schematic and photograph of Banbury mixer in tire manufacturing. Reproduced from technical document from Farrel corporation.	52
Figure 1.32. Fate of zinc oxide in tire.	53
Figure 1.33. Examples of methanol synthesis converters: (a) tube-cooled, low-pressure reactor; (b) quench-cooled, low-pressure reactor [224]. Adopted from Catalyst Handbook, ed. M.V. Twigg, Manson Publishing Company, London, 1996).	60
Figure 1.34. a. An industrial desulfurisation unit; b. A schematic diagram of a simplified hydrocarbon feedstock purification unit using ZnO as a desulfurisation absorbent; c. An example of a ZnO desulfurisation absorbent. By permission from Haldor Topsøe, Denmark.	62
Figure 1.35. (a) Schematic of microstructure of a ZnO varistor [10]; (b) small size varistor; (c) temperature dependence of I-V curve of ZnO varistor [232] and (d) a typical silicone-rubber-housed ZnO surge arrester type PEXLIM P330-YH420 suitable for protection in 420 kV systems by permission from ABB, Sweden.	64
Figure 1.36. PFD of production of zinc phosphate from zinc oxide.	68
Figure 1.37. PFD of production of zinc borate from zinc oxide.	69
Figure 2.1. Thermodynamic parameters for the reaction of solid $\epsilon\text{-Zn}(\text{OH})_2$ to solid ZnO and H_2O . The values are computed from the standard states at 298 °K at 1 atmosphere using the specific heat capacities from reference [287].	79
Figure 2.2. X-ray diffraction data obtained from the products of reactions A, B and C. The diffraction pattern for product C corresponds to pure ZnO (wurtzite). The peaks assigned to ZnO are indicated by * in the data for A and B. Other peaks in A and B correspond to $\epsilon\text{-Zn}(\text{OH})_2$.	83
Figure 2.3. XRD on the products of reactions (D) to (H) shows patterns, which conform with zinc oxide.	83
Figure 2.4. Thermogravimetric analysis data for the products of Reactions A, B and C. Heating rate was $5\text{ }^\circ\text{C min}^{-1}$ in an N_2 atmosphere.	84

Figure 2.5. TGA comparison charts on the products of reactions (C) to (H) shows no decomposition at 120 °C. Mass loss up to the temperature of 120 °C is attributed to moisture removal and the mass loss over 120 °C is attributed to surface hydroxyl groups removal.	84
Figure 2.6. SEM images of the products of reactions A (left) and B (right). From reaction (A) smaller ellipsoidal particles are formed on top of the big plate-like structures. In (B), plate-like structures cannot be detected and smaller star-like particles are dominant.	85
Figure 2.7. SEM images of ZnO particles produced by the reactions C to H.	86
Figure 2.8. XRD associated with zinc hydroxide sulphate tetrahydrate, $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}$ (JCPDF card 00-044-0673).	87
Figure 2.9. TGA on the as-produced $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}$	87
Figure 2.10. XRD data of the reaction products prepared at 70 °C using different feeding methods: (a) NaOH solution added to ZnSO_4 solution in a single addition; (b) NaOH solution added to ZnSO_4 solution in a dropwise manner; (c) ZnSO_4 solution added to NaOH solution in a single shot; (d) ZnSO_4 solution added to NaOH solution in a dropwise manner.	88
Figure 2.11. SEM images of ZnO particles produced at 70 °C with different feeding methods. (a) NaOH solution added to ZnSO_4 solution in a single addition; (b) NaOH solution added to ZnSO_4 solution in a drop-wise manner; (c) ZnSO_4 solution added to NaOH solution in a single addition; (d) ZnSO_4 solution added to NaOH solution in a drop-wise manner.	89
Figure 2.12. XRD shows ZnO hexagonal wurtzite structure for all the samples made at different temperatures from 25 °C to 90 °C.	91
Figure 2.13. SEM images of ZnO particles synthesised at different temperatures.	92
Figure 2.14. BET specific surface area (m^2/g) vs. reaction temperature in the range of 25 to 90 °C. The trend line shown was obtained by polynomial regression and is provided as a guide to the eye.	93
Figure 2.15. RT fluorescence emission spectra of ZnO powder samples: French process ZnO; (I) ZnO product where the zinc sulphate solution was added to the sodium hydroxide solution in a drop-wise manner over 3 minutes according to Section 2.3.2; (II) and (III) ZnO products from reactions at 80 °C and 60 °C according to Section 2.3.3, respectively. Excitation wavelength = 310 nm, excitation slit width = 5 nm (little steps at 460 and 570 nm are artefacts due to filter changes).	94
Figure 3.1. X-ray diffraction data obtained from the product of reaction between zinc sulphate and ammonia correspond to pure ZnO (wurtzite), JCPDF card 01-089-7102.	103
Figure 3.2. TGA on the ZnO product. Mass loss up to the temperature of 120 °C is attributed to moisture removal and the mass loss over 120 °C is attributed to removal of surface hydroxyl groups.	103
Figure 3.3. SEM images of zinc oxide crystals produced at 65 °C by feeding the zinc sulphate in a drop-wise manner to the ammonia solution.	104
Figure 3.4. RT fluorescence emission spectra of ZnO powder sample made by drop-wise addition of zinc sulphate solution to ammonia over 3 minutes according to section 3.2. Excitation wavelength = 310 nm, excitation slit width = 5 nm (little steps at 460 and 570 nm are artefacts due to filter changes).	105
Figure 4.1. XRD on (bottom) product of the reaction between zinc acetate and hydrogen peroxide corresponds to zinc peroxide (JCPDF card 01-077-2414) and (top) product of calcination of as-produced	

zinc peroxide corresponds to zinc oxide (JCPDF card 01-075-0576). Peaks marked with “*” are associated with zinc peroxide.....	113
Figure 4.2. XRD on (bottom) product of the reaction between $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}$ and H_2O_2 corresponds to ZnO_2 (JC-PDF 01-077-2414) and (top) product of calcination of as-produced ZnO_2 corresponds to mainly to ZnO (JC-PDF 00-001-1136) and some remaining ZnO_2 . Peaks marked with “*” are associated with zinc peroxide.	113
Figure 4.3. TGA on zinc peroxide made from (I) zinc acetate- H_2O_2 route and (II) $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}$ - H_2O_2 route.	114
Figure 4.4. DTA on zinc peroxide made from (I) zinc acetate- H_2O_2 route and (II) $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}$ - H_2O_2 route.	115
Figure 4.5. SEM image on nano-particles of ZnO_2 made via zinc acetate- H_2O_2 route.	116
Figure 4.6. SEM image on ZnO particles made via zinc acetate- H_2O_2 route.	116
Figure 4.7. SEM image on ZnO_2 made via $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}/\text{H}_2\text{O}_2$ route.	117
Figure 4.8. SEM images on ZnO/ZnO_2 particles made via $\text{Zn}_4\text{SO}_4(\text{OH})_6 \cdot 4\text{H}_2\text{O}-\text{H}_2\text{O}_2$ route.	117
Figure 5.1. XRD ($\text{Cu K}\alpha$) on the product corresponding to hydrozincite (JC-PDF card 00-019-1458). The peaks are broad.....	126
Figure 5.2. TGA-DTA on hydrozincite.	127
Figure 5.3. XRD ($\text{Cu K}\alpha$) on the calcined product corresponds to ZnO (JC-PDF card 00-005-0664). ..	127
Figure 5.4. SEM images of (A) BZC; (B) highly porous ZnO produced from calcination of BZC.	128
Figure 5.5. TEM images on the ZnO particles produced from calcination of BZC (courtesy of Dr A. Dowd).....	128
Figure 5.6. Colour-coded contour XRD (synchrotron) graph shows the real-time transformation of hydrozincite to ZnO . The intensity is colour-coded.	129
Figure 5.7. Two projections of 3D-stacked XRD (synchrotron) patterns on BZC show that intensity of BZC is lower than that of the end-product ZnO . ZnO peaks are intensified by increasing the temperature.	130
Figure 5.8. XRD ($\text{Cu K}\alpha$) on the products of calcination of BZC at a temperature range of 250-350 °C for 1 hour shows only ZnO peaks.	131
Figure 5.9. BET specific surface area of ZnO samples prepared by calcination of BZC at 250-350 °C.	131
Figure 5.10. XRD ($\text{Cu K}\alpha$) on the BZS tetrahydrate and the phase, which is believed to be BZS monohydrate.....	133
Figure 5.11. TGA on BZS tetrahydrate and monohydrate.	133
Figure 5.12. DTA on BZS tetrahydrate and monohydrate.	134
Figure 5.13. Colour-coded contour XRD (synchrotron) graph shows the real-time transformation of $\text{BZS} \cdot 4\text{H}_2\text{O}$ to ZnO . The intensity is colour-coded.	134
Figure 5.14. Two projections of 3D-stacked XRD (synchrotron) graphs on $\text{BZS} \cdot 4\text{H}_2\text{O}$	135
Figure 5.15. Top pattern: XRD pattern on the calcined $\text{BZS} \cdot 4\text{H}_2\text{O}$ at 113 °C obtained by synchrotron radiation (synchrotron 2θ values are converted to the equivalent of $\text{Cu K}\alpha$). Bottom pattern: XRD ($\text{Cu K}\alpha$) pattern on unidentified BZS. The two patterns match perfectly with each other.	136

Figure 5.16. Stacked XRD (synchrotron) on the BZS·4H ₂ O under calcination shows a dynamic phase transformation due to the dehydration by increasing the temperature.....	137
Figure 5.17. XRD pattern on the calcine at 204 °C obtained by synchrotron radiation (synchrotron 2 θ value is converted to its equivalent of Cu K α).	137
Figure 5.18. XRD pattern on the calcined sample at 555 °C obtained by synchrotron radiation (synchrotron 2 θ value is converted to its equivalent of Cu K α). ZnO peaks (JC-PDF 01-089-7102) are indicated by “*”. The remaining peaks have been identified as Zn ₅ O ₂ (SO ₄) ₃ (JC-PDF 00-016-0305)....	139
Figure 5.19. TGA-MS graphs on aged BZS·H ₂ O. Shown ion intensities for H ₂ O, O ₂ , CO ₂ , SO ₂ and SO ₃ are $\times 10^9$, $\times 10^{10}$, $\times 10^{11}$, $\times 10^{10}$ and $\times 10^{13}$, respectively.	140
Figure 5.20. XRD on the product of calcination of BZS at 900 °C shows ZnO peaks.....	141
Figure 5.21. SEM images on (A) precursor and (B) ZnO particles made from that.....	141
Figure 5.22. XRD results on (a) BZCl; (b) calcined BZCl for 2 hours at 400 °C; (c) calcined BZCl for 6 hours at 400 °C and (d) calcined BZCl for 6 hours at 400 °C plus 4 hours at 600 °C. Peaks marked with ♠ in (b) and (c) correspond to ZnO·ZnCl ₂ ·2H ₂ O and the peaks indicated with ♣ correspond to Zn ₅ (OH) ₈ Cl ₂ ·H ₂ O.....	147
Figure 5.23. SEM images of (A) BZCl and (B) ZnO made of that.	148
Figure 5.24. Colour-coded contour XRD (synchrotron) graph shows the real-time transformation of BZCl to ZnO. The intensity is colour-coded.....	148
Figure 5.25. Two projections of 3D-stacked XRD (synchrotron) graphs on BZCl.....	149
Figure 5.26. TGA-DTA on the freshly made BZCl and aged BZCl after 13 months.....	150
Figure 5.27. TGA-MS graph on aged BZCl under air atmosphere with a heating rate of 3 °C min ⁻¹ . Shown I_{18} for H ₂ O, I_{36} for HCl, I_{44} for CO ₂ and I_{136} for ZnCl ₂ are $\times 10^9$, $\times 10^{12}$, $\times 10^{11}$ and $\times 10^{14}$, respectively.	153
Figure 5.28. Sublimation set-up to trap the volatile zinc-containing material.....	154
Figure 5.29. TGA-DTA on ZnCl ₂ ·2H ₂ O and ZnCl ₂ sublimate collected.	155
Figure 5.30. XRD conducted at 100-120 °C and time per step = 5.6 s on the zinc-containing sublimate matches with α and β -zinc chlorides. Peaks marked with * are associated with β -ZnCl ₂ (JC-PDF 01-072-1284) and the rest are related to α -ZnCl ₂ (JC-PDF 01-074-0519) with major peaks located at 2 θ = 18.5 ° and 29 °.	155
Figure 5.31. XRD results on (bottom graph) BZN; (middle graph) calcined BZN for 1 hour at 250 °C; (top graph) calcined BZN for 1 hour at 250 °C plus 1 hour at 300 °C.	158
Figure 5.32. SEM images of (A) BZN and (B) ZnO made of that.	158
Figure 5.33. Colour-coded contour XRD (synchrotron) graph shows the real-time transformation of BZN to ZnO. The intensity is colour-coded.....	159
Figure 5.34. Two projections of 3D-stacked XRD (synchrotron) graphs on BZN.....	160
Figure 5.35. TGA-DTA on BZN.....	161
Figure 5.36. TGA-MS graphs for MS1. I_{12} for C ⁺ and I_{44} are shown $\times 10^{12}$ and $\times 10^{11}$, respectively. I_{18} for H ₂ O, I_{32} for O ₂ , I_{30} for NO, I_{46} for NO ₂ and I_{63} for HNO ₃ are shown $\times 10^9$, $\times 10^{10}$, $\times 10^{10}$, $\times 10^{12}$ and $\times 10^{14}$, respectively.	162

Figure 5.37. TGA-MS graphs for MS2. I_{18} for H_2O , I_{30} for NO, I_{46} for NO_2 and I_{32} for O_2 are shown $\times 10^9$, $\times 10^{10}$, $\times 10^{11}$ and $\times 10^{12}$, respectively.	162
Figure 5.38. TGA-MS graphs for MS3. I_{44} ($\times 10^{11}$) for N_2O or CO_2 is indicated by ♣. I_{63} ($\times 10^{14}$) for HNO_3 by ♠ and I_{30} ($\times 10^{10}$) for NO is indicated ♥ by and I_{46} ($\times 10^{11}$) for NO_2 is indicated by ♦. I_{18} for H_2O and I_{32} for O_2 are Shown $\times 10^9$ and $\times 10^{10}$, respectively.	163
Figure 5.39. TGA-MS graphs for MS4. I_{18} for H_2O and I_{30} for NO and I_{46} for NO_2 are shown $\times 10^9$, $\times 10^{10}$ and $\times 10^{10}$, respectively.	163
Figure 5.40. TGA-MS graphs for MS5. I_{44} and I_{18} for H_2O and I_{32} for O_2 and I_{63} for HNO_3 are shown $\times 10^{10}$, $\times 10^9$ and $\times 10^{13}$, respectively. Shown I_{30} for NO and I_{46} for NO_2 are $\times 10^{10}$ and $\times 10^{11}$, respectively.	164
Figure 5.41. I_{18} (H_2O^+) curves for various heating rates.	165
Figure 5.42. TGA comparative graphs obtained during TGA-MS tests.	166
Figure 5.43. Fraction of ionic currents for NO (X), NO_2 (Y) and O_2 (Z) vs. rate of heating.	167
Figure 5.44. TGA-MS on $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ under argon with a heating rate of 4°C min^{-1} . It can be seen that decomposition of $\text{Zn}(\text{NO}_3)_2$ undergoes completion at temperatures over 324°C with the release of nitrogen oxide species. I_{18} for H_2O , I_{32} for O_2 , I_{30} for NO, I_{46} for NO_2 and I_{44} are shown $\times 10^9$, $\times 10^9$ and $\times 10^9$, $\times 10^{10}$ and $\times 10^{10}$, respectively.	168
Figure 5.45. X-ray diffraction pattern of as-synthesised BZA. The positions of d -spacings at 1.42 and 1.49 nm are resolved from synchrotron data using Split-Pearson VII distribution function.	176
Figure 5.46. XRD (Cu $K\alpha$) on the product shows peaks associated with ZnO.	177
Figure 5.47. SEM images of (A) BZA and (B) the calcination product, ZnO.	177
Figure 5.48. Transmission electron images of the ZnO nanocrystals formed by calcination at 400°C . The characteristic hexagonal crystal habit of ZnO is clearly visible in some of the larger particles (courtesy of Dr A. Dowd).	178
Figure 5.49. FTIR spectrum of BZA dihydrate.	179
Figure 5.50. CP-MAS ^{13}C NMR spectra of BZA.	180
Figure 5.51. TGA-DTA in air on BZA with heating rate of 5°C min^{-1}	181
Figure 5.52. Colour-coded contour graphs generated from XRD (synchrotron) data show the real-time transformation of BZA to ZnO. The intensity is colour-coded. Top and bottom contour graphs show different ranges of 2θ vs. temperature.	182
Figure 5.53. 3D-stacked XRD (synchrotron) graphs from different views and in different ranges of temperatures for clarity.	183
Figure 5.54. XRD data collected from 27 to 113°C in a synchrotron. 2θ values are converted to corresponding Cu $K\alpha$ values for comparison reasons. Peaks marked with * correspond to ZnO and stick lines correspond to anhydrous zinc acetate (JC-PDF 00-001-0089).	184
Figure 5.55. XRD (Cu $K\alpha$) on the product collected after heating at 90°C shows the presence of ZnO mixed with anhydrous zinc acetate and a phase reported to be $\text{Zn}_3(\text{OH})_4(\text{Ac})_2$	186
Figure 5.56. TGA-MS data produced by the decomposition of aged zinc hydroxy acetate under argon atmosphere at a heating rate of 3°C min^{-1} . Channels I_{44} (CO_2), I_{18} (H_2O), I_{32} (O_2), I_{60} (acetic acid) and I_{58}	

(acetone) are scaled $\times 10^{10}$, $\times 10^9$, $\times 10^{10}$ and $\times 10^{12}$ and $\times 10^{11}$, respectively. (Channel I_{102} (acetic anhydride) data comes from a separate but similar sample of BZA to the other data (scaled $\times 10^{14}$)).	187
Figure 5.57. TGA-DTA on zinc acetate dihydrate in air. (I) heating rate: $1\text{ }^{\circ}\text{C min}^{-1}$ and (II) heating rate $5\text{ }^{\circ}\text{C min}^{-1}$.	190
Figure 5.58. Sublimation apparatus to trap the volatile zinc-bearing material.	191
Figure 5.59. XRD of the sublimate collected during thermal decomposition of dehydrated BZA.	192
Figure 5.60. SEM images of the sublimate.	192
Figure 5.61. XRD on (I) BZA and (II) the freeze-dried product of the reaction between BZA and ethanol. Peaks marked with '*' correspond to ZnO (JC-PDF 01-089-0510).	194
Figure 5.62. TGA on (I) BZA and (II) the freeze-dried product of the reaction between BZA and ethanol.	195
Figure 5.63. DTA on (I) BZA and (II) the freeze-dried product of the reaction between BZA and ethanol.	195
Figure 5.64. Raman spectra corresponding to (I) BZA and (II) product of the reaction between BZA and ethanol, freeze-dried for 24 hours.	197
Figure 5.65. FT-IR spectra corresponding to (I) BZA and (II) product of the reaction between BZA and ethanol, freeze-dried for 24 hours.	198
Figure 5.66. CP-MAS ^{13}C NMR spectrum of the product of the reaction between BZA and ethanol, freeze-dried for 24 hours.	199
Figure 5.67. TGA in air on basic zinc salts with heating rate of $5\text{ }^{\circ}\text{C min}^{-1}$.	200
Figure 5.68. XRD (synchrotron) on the precursor basic zinc salts.	201
Figure 5.69. XRD (synchrotron) on the end-products of the corresponding basic zinc salts at the maximum temperature during synchrotron radiation study. (Data have been normalised to beam intensity here and everywhere else in this thesis).	202
Figure 5.70. Fluorescence emission spectra of ZnO powder samples made from: (I) basic zinc carbonate at $300\text{ }^{\circ}\text{C}$; (II) basic zinc sulphate at $900\text{ }^{\circ}\text{C}$; (III) basic zinc acetate at $400\text{ }^{\circ}\text{C}$; (IV) basic zinc nitrate at $400\text{ }^{\circ}\text{C}$; (V) basic zinc chloride at $600\text{ }^{\circ}\text{C}$. (VI) is emission spectrum of commercial Zn:ZnO phosphor as a control. Excitation wavelength = 280 nm , excitation slit width = 5 nm (little steps at 460 and 570 nm are artefacts due to filter changes).	203
Figure 5.71. RT fluorescence emission spectra of ZnO powder samples made from: (I) basic zinc carbonate at $300\text{ }^{\circ}\text{C}$; (II) basic zinc sulphate at $900\text{ }^{\circ}\text{C}$; (III) basic zinc acetate at $400\text{ }^{\circ}\text{C}$; (IV) basic zinc nitrate at $400\text{ }^{\circ}\text{C}$; (V) basic zinc chloride at $600\text{ }^{\circ}\text{C}$. (VI) is the emission spectrum of commercial Zn:ZnO phosphor as a control. Excitation wavelength = 310 nm , excitation slit width = 5 nm (little steps at 460 and 570 nm are artefacts due to filter changes).	203
Figure 5.72. Colour-coded (top) 3D contour and (bottom) 2D top RT fluorescence emission spectra of Zn:ZnO phosphor vs. excitation wavelength from 300 to 400 nm .	204
Figure 6.1. XRD on the products of Reactions A - D and the precipitate from the filtrate of Reaction A.	213
Figure 6.2. TGA of the products of Reaction A-D and the precipitate from the filtrate of Reaction A.	215

Figure 6.3. DTA of the products of Reaction A to D and the precipitate from the filtrate of Reaction A (graphs are offset for clarity).....	216
Figure 6.4. SEM images on the zinc hydroxy nitrate precipitated from the filtrate of Reaction A.	217
Figure 6.5. Gibbs free energy of Reaction 6.9 is positive at $t = 0$. As time passes, it becomes negative (over $t_{eq} \approx 20$ minutes) and reaches its minimum at around 75 minutes. Then it approaches zero again at around 180 minutes due to the change in Q_r (as a result of changes in concentrations of the species in solution).	222
Figure 6.6. XRD patterns of the samples collected in the course of reaction.	223
Figure 6.7. TGA on the samples collected in the course of reaction.	224
Figure 6.8. DTA on the samples collected in the course of reaction (graphs are offset for clarity).	224
Figure 6.9. Graph of $\ln(\ln(\text{conversion}))$ vs. $\ln(\text{time})$ is not linear.	225
Figure 6.10. Sigmoid function curve fitting for conversion vs. time and the 1 st and 2 nd derivatives of the fitted curve vs. time. Maximum rate of conversion was shown to be at around 75 minutes.	225
Figure 6.11. SEM images on the samples collected at times 2, 5, 10 and 15 minutes in the course of reaction.....	227
Figure 6.12. SEM images on the samples collected at times 20 to 240 minutes in the course of reaction.	228
Figure 6.13. Schematic of the suggested mechanism for the solid/liquid reaction between ZnO and zinc nitrate solution. H^+ shows a catalytic role in this system.	231

List of Tables

	Page
Table 1.1. Typical properties of different grades of zinc oxide according to ASTM D4295-89 [44]. Reproduced with permission, from ASTM D4295-89 (2005) Standard Classification for Rubber Compounding Materials-Zinc Oxide, copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428.	11
Table 1.2. Industrial grades of zinc oxide. Data are adapted from the product datasheets from industrial producers: PT. Indo Lysaght Indonesia, US Zinc in the USA, Umicore Zinc Chemicals and Silox in Belgium, IEQSA in Peru and Grillo Zinkoxid GmbH in Germany.	43
Table 1.3. Skincare products containing active ZnO vs. its percentage in the formulation [212].	58
Table 2.1. Zinc sulphate to sodium hydroxide mole ratio. The pH of the resultant mixtures after reaction was in the range of 11 to 12.	81
Table 5.1. Calcination conditions to produce ZnO using basic zinc salt precursors.	125
Table 5.2. TGA-MS experiments conditions and species tested.	161
Table 5.3. Ion intensity fraction for NO (X), NO ₂ (Y) and O ₂ (Z) vs. rate of heating.	166
Table 5.4. Layered zinc hydroxy-acetates of the Zn _x (OH) _y Ac _z ·nH ₂ O family, Ac = acetate [CH ₃ CO ₂] ⁻ . The interlayer <i>d</i> -spacings are obtained from the text of the source or by analysing the published X-ray diffraction pattern.	172
Table 5.5. FTIR spectral assignments for BZA.	179
Table 5.6. BET specific surface area of the ZnO powder samples vs. precursor salt and calcination temperature.	205
Table 6.1. Mole ratios of the reactants and pH data.	211
Table 6.2. Reaction data from solid/liquid reactions between ZnO and Zn(NO ₃) ₂	215
Table 6.3. Difference between the measured and calculated equilibrium pH of zinc nitrate solution. The pH is calculated based on the hydrolysis reaction $\text{Zn}^{2+}_{(aq)} + \text{H}_2\text{O} \rightleftharpoons \text{ZnOH}^{+}_{(aq)} + \text{H}^{+}_{(aq)}$	219
Table 6.4. Solubility products of some zinc compounds compared to the reported values for zinc hydroxy nitrate in the current work.	230

List of Schemes

	Page
Scheme 2.1. Thermodynamic data for the formation of ZnO from Zn^{2+} and OH^- at 298 °K and 1 atm. Standard states have been assumed. For consistency, data from Zhang and Muhammed were used [289].	97
Scheme 3.1. Thermodynamic data for the formation of ZnO from Zn^{2+} -water-ammonia system at 298 °K and 1 atm. Standard states have been assumed. Data adopted from [89, 285, 289].	107
Scheme 5.1. Schematic of suggested mechanism for thermal transformation of $\text{BZS} \cdot 4\text{H}_2\text{O}$ into ZnO. Dotted arrows show partial side reaction.	142
Scheme 5.2. Schematic of suggested mechanism for thermal transformation of BZCl into ZnO. Partial side reaction is indicated by dotted arrow, which is responsible for the excess of mass loss during some TGA experiments.	156
Scheme 5.3. Schematic of suggested mechanism for thermal transformation of BZN to ZnO. Dotted arrows represent probable side reactions that are not balanced.	169
Scheme 5.4. Schematic of suggested mechanism for thermal transformation of $\text{BZA} \cdot 2\text{H}_2\text{O}$ to ZnO. Dotted arrows show side reactions.	193

Abbreviations

α_L = coefficient of expansion

λ = thermal conductivity value

Ac = acetate (CH_3CO_2^-)

ASTM = American Society for Testing and Materials

a.m.u = atomic mass unit

BAW = bulk acoustic wave

BET = Brunauer, Emmett and Teller

BZA = basic zinc acetate

BZC = basic zinc carbonate

BZCl = basic zinc chloride

BZN = basic zinc nitrate

BZS = basic zinc sulphate

CHM = composite hydroxide mediated

C_p° = specific heat capacity

CP-MAS = cross polarisation magic angle spinning

cr = crystalline

CRT = cathode ray tube

CVD = chemical vapor deposition

D2EHPA = di-2-ethyl hexyl phosphoric acid

DMS = dilute magnetic semiconductors

DSC = dust settling chamber

DTA = Differential thermal analysis

E_a = apparent activation energy

EAFD = electric arc furnace dust

EG = ethylene glycol

ENR = epoxidised natural rubber

EPDM = ethylene propylene diene monomer

FID = Free induction decay

FTIR = Fourier transform infrared

FWHM = Full width at half maximum

G = Gibbs free energy

GTL = gas-to-liquid

H = Enthalpy

H₂O₂ = hydrogen peroxide

HCE = hexachloroethane

HDPE = high density polyethylene

HDS = hydroxy double salts

HVPE = hydride vapor phase deposition

ICP-MS = Inductively coupled plasma mass spectrometry

ISP = imperial smelting process/irregularly-shaped particle

ITO = indium tin oxide

K_{atm} = equilibrium constant

LDH = layered double hydroxide

LED = light emitting diodes

MBE = molecular beam epitaxy

MBT = mercaptobenzothiazole

MCP = mechano-chemical process

MOCVD = metal organic chemical vapor deposition

MS = mass spectrometry

M.W = molecular weight

$\text{Na}_2\text{S}_2\text{O}_4$ = sodium dithionite

$\text{NaHSO}_2 \cdot \text{CH}_2\text{O} \cdot 2\text{H}_2\text{O}$ = sodium formaldehyde sulfoxylate

NMR = Nuclear magnetic resonance

OECD = Organisation for Economic Cooperation and Development

PFD = process flow diagram

phr = parts per hundred

PMA = polymer-modified asphalts

PP = polypropylene

ppb = parts per billion

ppm = parts per million

PVC = poly vinyl chloride

PVDF = polyvinylidene fluoride

rpm = revolutions per minute

RT = room temperature

SAW = surface acoustic wave

SRB = sulphate-reducing bacteria

SEM = scanning electron microscopy

SHG = special high grade

s-SBR = solution styrene-butadiene rubber

SVP = seeded vapor phase

T = temperature

TCO = transparent conductive oxides

TE = thermoelectric

TEM = transmission electron microscopy

TG = thermogravimetric

TGA = thermogravimetric analysis

TMTD = tetra-methyl-thiuramdisulphide

UV = ultra violet

VLS = vapor-liquid-solid

VPT = vapor phase transport

VS = vapor-solid

w/v = weight to volume

w/w = weight to weight

XNBR = carboxylated nitrile rubber

XRD = X-ray diffraction

ZnAc₂ = zinc acetate

Zn(CH₃COO)₂·2H₂O = zinc acetate dihydrate

ZDDP = Zinc dialkyldithiophosphate

ZnSO₄·7H₂O = zinc sulphate heptahydrate

ZT = figures-of-merit

Publications and conference presentations associated with this work

1. Moezzi, A., “Nano vs. Active Zinc Oxide”. Presentation at the International Conference on Nanosciences and Nanotechnology (ICONN), Sydney, Australia, February 2010.
2. Moezzi, A., Cortie, M and McDonagh, A. “Aqueous pathways for the formation of zinc oxide nanoparticles”. Dalton Transactions **40**(18) (2011) 4871-4878.
3. Moezzi, A., Cortie, M and McDonagh, A. “Zinc Oxide Particles: Synthesis, Properties and Applications”. Chemical Engineering Journal **185-186** (2012) 1-22.

Abstract

Zinc oxide is an important material industrially and scientifically. It has a long history dating back to more than four thousand years ago. It has applications in rubber production, cosmetics, pigments and ceramics. The properties of zinc oxide such as porosity, specific surface area and optical properties change as a result of changing the synthetic method and process conditions. The suitability of ZnO for different applications depends on the properties of the material, which in turn are influenced by synthetic routes.

Knowledge of the processes underpinning the various synthetic techniques is key to understanding the properties of the ZnO end-product. In this work, various synthetic techniques have been investigated that may be amenable to large-scale production. The resultant materials were studied and important insights were obtained. For example, it was found that the precursor materials and method of processing for the production of zinc oxide have important roles in controlling the properties of the product such as specific surface area, crystal morphology, particle size and amount of surface hydroxyl groups embedded in the product.

In single-stage production methods, zinc oxide is precipitated directly from a zinc solution. Influences of reaction temperature, concentration of the reactants and feeding techniques on the properties of the products were determined.

In multi-stage routes, intermediate zinc-bearing materials including zinc peroxide and zinc hydroxy carbonate, sulphate, chloride, nitrate and acetate were synthesised. These intermediate materials were then used as precursors for the formation of zinc oxide particles. Relationships between the properties of the precursor zinc-containing compound and the end-product zinc oxide were studied and unexpected results were obtained. For example, it was shown that specific surface area of the zinc oxide product depends significantly on the precursor material from which it is produced. Techniques were investigated that can produce multiple important zinc-bearing compounds and it was found that it could be engineered by selection of the appropriate precursors and process conditions.